

No.: GZIN2008043533MR

Date: Aug 20, 2020

Page: 1 of 5



CUSTOMER NAME: RAXWELL INDUSTRIAL TECHNOLOGY (SHANGHAI) CO., LTD.

ADDRESS: 3501, 5F SUNPLUS BUILDING, NO.1077 ZUCHONGZHI RD PU DONG

NEW DISTRICT, SHANGHAI

Sample Name : POLYETHYLENE FOIL-0.08mm

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

SGS Ref. No. : GZHL2008042649OT

Date of Receipt : Aug 14, 2020
Testing Start Date : Aug 14, 2020
Testing End Date : Aug 20, 2020

Test result(s) : For further details, please refer to the following page(s)

(Unless otherwise stated the results shown in this test report refer only to

the sample(s) tested)

Signed for SGS-CSTC Standards Technical Services Co., Ltd. GZ Branch Testing

Kelly Lee

Authorized signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printeroverleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx.and, for electronic format documents subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/rerms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to create the company of the company. Any unauthorized alteration, forgery or falsification of the content of appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

**Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443



No.: GZIN2008043533MR

Date: Aug 20, 2020

Page: 2 of 5

Summary of Results:

No.	Test Item	Test Method Result		Conclusion
	Tensile Strength and	GB/T 4456-2008 Section		
1	Nominal Tensile Strain at	5.6.1 & GB/T 1040.3-	See result	/
	Break	2006		

Note: Pass : Meet the requirements;

Fail: Does not meet the requirements;

/: Not Apply to the judgment.

Original Sample Photo:





Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification in and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sss.com



No.: GZIN2008043533MR

Date: Aug 20, 2020

Page: 3 of 5

Test Item: Tensile Strength and Nominal Tensile Strain at Break

Sample Description: Film

Test Method: GB/T 4456-2008 Section 5.6.1 & GB/T 1040.3-2006

Test Condition:

Specimen: Type 2

Specimen width: 10mm

Specimen thickness: 0.082mm Testing speed: 500mm/min

Initial distance between grips: 100mm

Lab Environmental Condition: (23 ± 2) °C, (50 ± 5) % RH

Test Result:

Test Item	Test Result		
Tensile Strength	MD	26.9MPa	
Torione outeright	CD	25.8MPa	
Nominal Tensile Strain at Break	MD	740%	
Tronmar Tonono Guant at Break	CD	810%	

Note: Test specimens were cut from the sample.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is dorawn to the limitation of liability, indemnification in and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to lite Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or fallsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the au. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

**Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443,



No.: GZIN2008043533MR


Date: Aug 20, 2020


Page: 4 of 5

Test Photo:



During test





After test-MD



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.aspx and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's Sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.


Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: Col. Doccheck@ss.com



No.: GZIN2008043533MR

Date: Aug 20, 2020

Page: 5 of 5



Equipment Information:

Equipment	Model	Equipment No.	Calibration date	Next Calibration date
Universal	71.0	GZMR-PL-E168	2020 04 40	2021-04-09
Testing Machine	Z1.0	GZIVIR-PL-E 100	2020-04-10	2021-04-09

Appendix information: The test report shall only be used for clients' scientific research, teaching, internal quality control, product research and development, etc., and just for internal reference.

****** End of report******



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions.spx, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions